

N A D I S

D E S I G N

TECHNICAL INFORMATION

Color Body Porcelain - Rectified

| | |
|-----------|---|
| MODEL | TIFFANY |
| COLOR | WHITE / BEIGE / GRAY / GRAPHITE (Color does not affect test results) |
| REAL SIZE | 450 x 900 mm |
| FINISH | SILK / NATURAL / ANTISLIP AS (For the different finishes see the test results) |
| THICKNESS | 10,4 mm |

UNE-EN 1441:2016

DRY-PRESSED CERAMIC TILE - UNGLAZED (UGL) - WATER ABSORPTION INFERIOR THAN 0.5% - Group Bla - Annex G

| STANDARD | ESSAY / FEATURES | REQUIRED | RESULT (*) |
|-----------------------|--|--------------------------|--|
| EN-ISO 10545 / 3 | Water absorption | $E \leq 0,5\%$ | $E \leq 0,3\%$ |
| EN-ISO 10545 / 4 | Bending strength | $\geq 35 \text{ N/mm}^2$ | $> 40 \text{ N/mm}^2$ |
| | Breaking strength | $\geq 1300 \text{ N}$ | $> 2000 \text{ N}$ |
| EN-ISO 10545 / 6 | Resistance to deep abrasion | 175 mm^3 | Complies |
| EN-ISO 10545 / 11 | Determination of crazing resistance | Required | Complies |
| EN-ISO 10545 / 12 | Determination of frost resistance | Required | Complies |
| EN-ISO 10545 / 13 | Resistance to chemical and swimming pool salts | Min UG/ UGL - B | UG / UGL - A |
| EN-ISO 10545 / 14 | Determination of resistance to stain | Min. Class 3 | Class 5 |
| UNE ENV 12633 | Slip resistance (Pendulum test) | Min. Class 1 | SILK 1 NATURAL 1 ANTISLIP AS 3 |
| DIN 51130 | Critical angle (Inclined platform test) | Min. R9 | SILK -- NATURAL R9 ANTISLIP AS R11 |
| DIN 51097 | Critical angle (Wet loaded barefoot test) | Min. Class A | SILK -- NATURAL A ANTISLIP AS A+B+C |
| UNE EN 13501 - 1:2002 | Reaction to fire | | A1 / A1FL |
| UNE EN 14021 - 1:2002 | Ecolabel and environmental statement | | 31 % |

(*) The declared values are the average obtained in the internal laboratory of different productions. (march 2021)



31 %



ES19/85847

NADIS DESIGN S.L.

T: +34 964 89 13 89 - www.nadisdesign.com - info@nadisdesign.com