

## TECHNICAL INFORMATION

## Color Body Porcelain - Rectified

MODEL	<b>JURA</b>	
COLOR	<b>LIGHT / BEIGE / GRAY</b>	(Color does not affect test results)
REAL SIZE	<b>598 x 598 mm</b>	
FINISH	<b>NATURAL / ANTISLIP AS</b>	(For the different finishes see the test results)
THICKNESS	<b>9,6 mm</b>	

### UNE-EN 1441:2016

DRY-PRESSED CERAMIC TILE - UNGLAZED (UGL) - WATER ABSORPTION INFERIOR THAN 0.5% - Group Bla - Annex G

STANDARD	ESSAY / FEATURES	REQUIRED	RESULT (*)
<b>EN-ISO 10545 / 3</b>	Water absorption	E ≤ 0,5%	E ≤ 0,3%
<b>EN-ISO 10545 / 4</b>	Bending strength	≥ 35 N/mm <sup>2</sup>	> 37 N/mm <sup>2</sup>
	Breaking strength	≥ 1300 N	> 1600 N
<b>EN-ISO 10545 / 6</b>	Resistance to deep abrasion	175 mm <sup>3</sup>	Complies
<b>EN-ISO 10545 / 11</b>	Determination of crazing resistance	Required	Complies
<b>EN-ISO 10545 / 12</b>	Determination of frost resistance	Required	Complies
<b>EN-ISO 10545 / 13</b>	Resistance to chemical and swimming pool salts	Min UG/ UGL - B	UG / UGL - A
<b>EN-ISO 10545 / 14</b>	Determination of resistance to stain	Min. Class 3	Class 5
<b>UNE ENV 12633</b>	Slip resistance (Pendulum test)	Min. Class 1	<b>NATURAL</b> 1 <b>ANTISLIP AS</b> 3
<b>DIN 51130</b>	Critical angle (Inclined platform test)	Min. R9	<b>NATURAL</b> R9 <b>ANTISLIP AS</b> R11
<b>DIN 51097</b>	Critical angle (Wet loaded barefoot test)	Min. Class A	<b>NATURAL</b> A <b>ANTISLIP AS</b> A+B+C
<b>UNE EN 13501 - 1:2002</b>	Reaction to fire		A1 / A1FL
<b>UNE EN 14021 - 1:2002</b>	Ecolabel and environmental statement		31 %

(\*) The declared values are the average obtained in the internal laboratory of different productions. (march 2021)



**31 %**



**ES19/85847**