

## TECHNICAL INFORMATION

## Color Body Porcelain - Rectified

|           |                                                                      |
|-----------|----------------------------------------------------------------------|
| MODEL     | <b>MONDO</b>                                                         |
| COLOR     | <b>LIGHT / GRAY / DARK GRAY</b> (Color does not affect test results) |
| REAL SIZE | <b>1198 x 2600 mm</b>                                                |
| FINISH    | <b>NATURAL</b>                                                       |
| THICKNESS | <b>5,6 mm</b>                                                        |

### UNE-EN 1441:2016

DRY-PRESSED CERAMIC TILE - UNGLAZED (UGL) - WATER ABSORPTION INFERIOR THAN 0.5% - Group Bla - Annex G

| STANDARD                     | ESSAY / FEATURES                               | REQUIRED                 | RESULT (*)            |
|------------------------------|------------------------------------------------|--------------------------|-----------------------|
| <b>EN-ISO 10545 / 3</b>      | Water absorption                               | $E \leq 0,5\%$           | $E < 0,3\%$           |
| <b>EN-ISO 10545 / 4</b>      | Bending strength                               | $\geq 35 \text{ N/mm}^2$ | $> 40 \text{ N/mm}^2$ |
|                              | Breaking strength                              | $\geq 700 \text{ N}$     | $> 1000 \text{ N}$    |
| <b>EN-ISO 10545 / 6</b>      | Resistance to deep abrasion                    | $175 \text{ mm}^3$       | Complies              |
| <b>EN-ISO 10545 / 11</b>     | Determination of crazing resistance            | Required                 | Complies              |
| <b>EN-ISO 10545 / 12</b>     | Determination of frost resistance              | Required                 | Complies              |
| <b>EN-ISO 10545 / 13</b>     | Resistance to chemical and swimming pool salts | Min.B                    | A                     |
| <b>EN-ISO 10545 / 14</b>     | Determination of resistance to stain           | Min. Class 3             | Class 5               |
| <b>UNE EN 13501 - 1:2002</b> | Reaction to fire                               |                          | A1 / A1FL             |
| <b>UNE EN 14021 - 1:2002</b> | Ecolabel and environmental statement           |                          | 23 %                  |

(\*) The declared values are the average obtained in the internal laboratory of different productions. (January 2025)



23 %



ES19/85847