

TECHNICAL INFORMATION

Color Body Porcelain - Rectified

MODEL	POLS	
COLOR	WHITE / SAND / GRAY / GRAPHITE / COPPER	(Color does not affect test results)
REAL SIZE	598 x 598 mm	
FINISH	NATURAL	
THICKNESS	8 mm	

UNE-EN 1441:2016

DRY-PRESSED CERAMIC TILE - GLAZED (GL) - WATER ABSORPTION INFERIOR THAN 0.5% - Group Bla - Annex G

STANDARD	ESSAY / FEATURES	REQUIRED	RESULT (*)	
EN-ISO 10545 / 3	Water absorption	$E \leq 0,5\%$	E < 0,5%	
EN-ISO 10545 / 4	Bending strength	$\geq 35 \text{ N/mm}^2$	> 35 N/mm ²	
	Breaking strength	$\geq 1300 \text{ N}$	> 1300 N	
EN-ISO 10545 / 6	Resistance to deep abrasion	175 mm ³	Complies	
EN-ISO 10545 / 11	Determination of crazing resistance	Required	Complies	
EN-ISO 10545 / 12	Determination of frost resistance	Required	Complies	
EN-ISO 10545 / 13	Resistance to chemical and swimming pool salts	Min.B	A	
EN-ISO 10545 / 14	Determination of resistance to stain	Min. Class 3	Class 5	
UNE ENV 12633	Slip resistance (Pendulum test)	Min. Class 1	NATURAL	2
DIN 51130	Critical angle (Inclined platform test)	Min. R9	NATURAL	R10
DIN 51097	Critical angle (Wet loaded barefoot test)	Min. Class A	NATURAL	A+B
UNE EN 13501 - 1:2002	Reaction to fire		A1	
UNE EN 14021 - 1:2002	Ecolabel and environmental statement		45 %	

(*) The declared values are the average obtained in the internal laboratory of different productions. (January 2025)



45 %



ES19/85847