

TECHNICAL INFORMATION

Color Body Porcelain - Rectified

MODEL	ALBOR	
COLOR	WHITE / CREAM	(Color does not affect test results)
REAL SIZE	600 x 1200 mm	
FINISH	SILK / NATURAL HAMMERED / ANTISLIP AS	(For the different finishes see the test results)
THICKNESS	9,2 mm	

UNE-EN 1441:2016

DRY-PRESSED CERAMIC TILE - GLAZED (GL) - WATER ABSORPTION INFERIOR THAN 0.5% - Group Bla - Annex G

STANDARD	ESSAY / FEATURES	REQUIRED	RESULT (*)
EN-ISO 10545 / 3	Water absorption	$E \leq 0,5\%$	$E \geq 0,5\%$
EN-ISO 10545 / 4	Bending strength	$\geq 35 \text{ N/mm}^2$	$> 35 \text{ N/mm}^2$
	Breaking strength	$\geq 1300 \text{ N}$	$> 1300 \text{ N}$
EN-ISO 10545 / 6	Resistance to deep abrasion	175 mm^3	Complies
EN-ISO 10545 / 11	Determination of crazing resistance	Required	Complies
EN-ISO 10545 / 12	Determination of frost resistance	Required	Complies
EN-ISO 10545 / 13	Resistance to chemical and swimming pool salts	Min.B	B
EN-ISO 10545 / 14	Determination of resistance to stain	Min. Class 3	Class 5
UNE ENV 12633	Slip resistance (Pendulum test)	Min. Class 1	NAT. HAMM. 2 ANTISLIP 3
DIN 51130	Critical angle (Inclined platform test)	Min. R9	NAT. HAMM. R10 ANTISLIP R11
DIN 51097	Critical angle (Wet loaded barefoot test)	Min. Class A	NAT. HAMM. A+B ANTISLIP A+B+C
UNE EN 13501 - 1:2002	Reaction to fire		A1
EN -ISO 10545 / 7	Abrasion Resistance (PEI)		WHITE IV CREAM IV
VOC	Do not release volatile elements		
UNE EN 14021 - 1:2002	Ecolabel and environmental statement		45%

(*) The declared values are the average obtained in the internal laboratory of different productions. (January 2025)



45 %



ES19/85847